

Glasurit COLOR-NET.

Manufacturer	Paint Line	Colour	Code	First year
VOLKSWAGEN - AUDI	21	TEXASGELB	L10B	72

Weight formula for 1.000 litre(s)

00	09/1983	1/B	AD2101
----	---------	-----	--------

Step 1	AD2101
M60	509.1
A115	746.2
M5	960.0
M77	1107.7
M974	1140.2

switch to Volume

Same colour with paint line 22

query

Copyright © 1999 Glasurit GmbH

ACRYLIC ENAMEL

REDUCTION: 3:1 to 2:1 using 8831/8832/8833/8834.
Note temp. range, 8:6:1 when using hardener.

AIR PRESSURE: 50-55 lbs. solids, 55-60 lbs. met.

FLASHTIME: 2-3 med. coats, 5-10 min. flash.

DRY: 10 min. dust free, 1 hr. tack free, 3 hrs. tape free.
With hardener 20 min. dust free, 3 hrs. tack free,
5-7 hrs. tape free.

MANUFACTURERS: 8850 med., 8870 slow, 8871 fast.
Res: 1003 for detailed information, refer to Product Data page 140558.

COLOR NUMBER: 99L 2146 /

MAKE & YEAR:

COLOR CODE:

COLOR NAME: Texas Yellow

FISHEYE 87 FLEX-AD 3034 RETARDER 88-0

PROPER BOX MUST BE MARKED.

LEAD FREE FORMULA

LEAD CONTAINING FORMULA

CAS No.	Ingredient
64742-88-7	Mineral Spirits
108-88-1	Toluene
100-41-4	Ethylbenzene
1330-20-7	Xylene
78-10-2	Methyl Ethyl Ketone
123-86-4	n-Butyl Acetate
112-67-2	2-Butyl Acetate
13463-67-7	Triphenyl Acetate
1344-37-7	Triphenyl Oxide
13256-85-6	Acrylic Polyester
	Lead Chromate
	Alkyd Resin

ALL FORMULA INFORMATION FOUND ON MICROFICHE.

H	2
FLAMMABILITY	3
F	0
REACTIVITY	J3
P	
HAZ-SAFE™ CODE	

VOC CONTENT MUST BE MARKED. REFER TO MICROFICHE FOR DETAILED INFORMATION.

VOC CONTENT AS PACKAGED: 4.37 lbs./gal

FOR PROFESSIONAL USE ONLY. NOT FOR RETAIL TRADE.

FOR DETAILED APPLICATION INSTRUCTIONS, REFER TO PRODUCT LABEL AND/OR THE MARTIN-SENOUR REFINISH MANUAL.

FORM NUMBER 214

3 coats
10/10/99 - 10/24/99
Jim Goodfry